



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] A 91 F

PROCESSING ADDITIVE

COMPOSITION

Mixture of zinc soaps of high molecular weight fatty acids.

PROPERTIES

Appearance	brownish-green to brown pastilles
Dropping Point (°C)	76-86
Specific Gravity	1.10
Zinc Content (% , max.)	15
Physiological Behavior	refer to safety data sheet
Storage Stability	at least 2 years under normal storage conditions
Packaging	55 lb. PE bags

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] A 91 F is used to reduce viscosity in NR and SBR.

DOSAGE

1 - 3 phr