



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] HPS 11

PROCESSING ADDITIVE

COMPOSITION

Blend of fatty acid derivatives.

PROPERTIES

Appearance	light tan pastille
Dropping Point (°C)	78 - 92
Specific Gravity	0.98
Physiological Behavior	refer to safety data sheet
Storage Stability	at least 2 years under normal storage conditions
Packaging	25 kg. PE bags

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] HPS 11 is the latest addition to our new high performance product line. It is composed of special fatty acid derivatives, which have been designed and selected to give maximum polymer to additive interactions. STRUKTOL[®] HPS 11 is effective in increasing flow, promoting release, and effectively acts to improve overall processing.

DOSAGE

1 to 2% of the total batch weight

(03/05/02)rca