



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] A 60 DH

PEPTIZER FOR NATURAL RUBBER

PROCESSING ADDITIVE FOR NATURAL AND SYNTHETIC RUBBER

COMPOSITION

Mixture of zinc soaps of high-molecular fatty acids.

PROPERTIES

Appearance	beige pastilles
Ash Content (% , max.)	14
Melting Point (°C)	75-95
Specific Gravity	1.15
Physiological Behavior	refer to safety data sheet
Storage Stability	at least 18 months under normal storage conditions.
Packaging	25 kg. PE bags

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] A 60 DH is a rubber soluble zinc soap leading to a faster physical peptization of natural rubber. It starts to be effective in the lower temperature range of compounding and can be used for mastication in a separate stage as well as for single stage mixing. STRUKTOL[®] A 60 DH can be used in all types of rubber.

STRUKTOL[®] A 60 DH affects the rapid incorporation of the fillers which leads to a shorter mixing cycle. The Shore hardness of the vulcanizates is not influenced.

Being rubber soluble, STRUKTOL[®] A 60 DH does not bloom from the vulcanizates. Reduction of high dosages of stearic acid or paraffins is possible.

DOSAGE

1 - 5 phr

(10/06/05)/rca