



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] CY 48

PROCESSING ADDITIVE

COMPOSITION

Blend of fatty acid derivatives.

TYPICAL PROPERTIES

| | |
|------------------------|--|
| Appearance | Off white to brown pastille |
| Dropping Point (°C) | 90 - 104 |
| Specific Gravity | 1.06 |
| Physiological Behavior | Refer to safety data sheet |
| Storage Stability | at least 2 years under normal storage conditions |
| Packaging | 55 lb. bag |

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] CY 48 is a recent addition to our line of processing and performance enhancing additives. It can be used in both natural & synthetic rubbers due to its selected composition comprising fatty acid derivatives with different polarities.

STRUKTOL[®] CY 48 is particularly suited for enhancing the properties and improving the processing behavior of silica containing compounds with and without coupling agents.

DOSAGE

1 – 5 phr