



## Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649  
Stow, Ohio 44224-0649 • www.struktol.com  
Phone (330) 928-5188 • Fax (330) 928-8726

## TECHNICAL DATA

# STRUKTOL<sup>®</sup> TPW 604\*

**PROCESSING ADDITIVE**

### COMPOSITION

Blend of an aliphatic carboxylic acid salts and mono and diamides.

---

### PROPERTIES

---

Appearance	Off-white to light tan pastille or bead
Dropping Point (°C)	95 - 113
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	25 kg. bags

---

### RECOMMENDATIONS FOR APPLICATION

STRUKTOL<sup>®</sup> TPW 604 is a unique blend of lubricants designed specifically for wood fiber/flour filled polyolefins. This product will provide improved surface quality, increased output rates and a wider processing window leading to overall improved processability.

STRUKTOL<sup>®</sup> TPW 604 can also be used in other polyolefin compounds where improved processability or output rates are required.

### DOSAGE

Typical usage levels are 2 – 7% of total compound weight.

*\* Only available in Eastern and Southern Pacific Rim Countries.*

(08/03/07)LCL/mmm

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.