



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] TPW 012

PROCESSING ADDITIVE

COMPOSITION

An optimized blend of special oleo chemicals and waxes.

PROPERTIES

| | |
|------------------------|--|
| Appearance | Beige to light tan pastilles |
| Dropping Point (°C) | 122°C - 128°C |
| Specific Gravity | 0.98 |
| Physiological Behavior | Refer to safety data sheet |
| Storage Stability | At least 2 years under normal storage conditions |
| Packaging | 55 lb. bag |

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TPW 012 is a formulated blend of lubricants designed to provide optimum processing, surface and physical property characteristics of rigid PVC compounds.

STRUKTOL[®] TPW 012 is recommended for wood-filled PVC and has been shown to provide significant processing and output rate benefits when compared to traditional lubricant formulations.

DOSAGE

2 – 8 parts depending on formulation and processing needs. Contact a Struktol technical service representative for more information.

(06/13/02)/rca