



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] TPW 426

PROCESSING ADDITIVE

COMPOSITION

Proprietary blend of fatty acid derivatives.

TYPICAL PROPERTIES

Appearance	Off white to light tan powder
Ash Content (%)	3.5 - 5.5
Dropping point (C)	104 - 113
Specific Gravity	0.99
Storage Stability	At least 2 years under normal storage conditions
Packaging	2000 lb SS

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TPW 426 offers superior wettability of fillers in compounds that use various types of fillers, filler combinations and particle size while providing significant processing improvements and output rate.

DOSAGE

Most manufacturers have found 1 to 5% of total compound weight gives excellent results.

(04/04/10)NK/rca