



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] TR 063A

PROCESSING ADDITIVE

COMPOSITION

Proprietary blend.

TYPICAL PROPERTIES

Appearance	Beige to off-white pastille
Dropping Point (°C)	105 - 120
Specific Gravity	1.227
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TR 063A is designed to provide improved processing characteristics of filled and unfilled polyamides. Typical improvements at the compounding stage are reduced die build-up (“die bearding”) and die drool. For injection molding applications, processors can expect to see better flow and mold filling vs. typical lubricants such as metal stearates or amide waxes.

DOSAGE

Typically 0.2 – 2.0% dependant on filler type and loading level.

(01/09/2012)MSF/ZB//rca