



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] TR 251 PROCESSING AGENT

COMPOSITION

A complex oleochemical mixture containing mono and di amides and metal soap.

PROPERTIES

Appearance	Beige pastille or prill
Dropping Point (°C)	115 - 125
Specific Gravity	.996
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag 165 lb. drum (prill only)

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TR 251 is a unique blend of anionic and ionic surfactant with lubricant designed for applications where EBS (ethyl bis-stearamide) is commonly used. These include ABS compounds, rigid PVC extrusions, color concentrates and other high-filled applications (e.g. calcium carbonate filled polypropylene). STRUKTOL[®] TR 251 has enhanced functionality over EBS with similar gloss properties.

STRUKTOL[®] TR 251 is also an efficient process aid in polyolefin, PVC, and ABS based wood composites where it enhances flow and improves fiber dispersion and surface quality. It can also be used as a processing aid and anti-stat in BOPP, PE and PP film.

ADDITION LEVELS

ABS, PVC & PS	0.5 – 2.0%
Wood Composites	1.0 – 3.0%
Olefins	< 0.5%
BOPP, PE & PP Film	< 3.0%

(04/20/12)SNK/JMB/mmm

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.