



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] TR EBS VG

**BLENDING AID
PROCESSING ADDITIVE**

COMPOSITION

N,N' Ethylene Bis-stearamide. STRUKTOL[®] TR EBS VG is manufactured from high quality vegetable acid with low iodine value.

PROPERTIES

Appearance	White bead, pastille or powder
Acid Value	< 10
Melting Point (°C)	135 - 150
Specific Gravity	0.98
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. PE bags

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TR EBS VG (vegetable grade) is an exceptionally effective dispersion aid, manufactured from vegetable source fatty acids for a wide range of organic and inorganic pigments.

STRUKTOL[®] TR EBS VG can be used in most polymer carrier systems.

ADDITION LEVELS

Varies by application. Please contact technical service at 1-800-327-8649 or 330-928-5188 for more information.

FDA STATUS

STRUKTOL[®] TR EBS VG is sanctioned for use by the Food and Drug Administration (FDA) in the following section of Title 21 of the Code of Federal Regulations:

175.105	Adhesives	177.1200	Cellophane
175.300	Resinous and polymeric coatings	177.1350	Ethylene-vinyl acetate copolymer
176.170	Components of paper and paperboard in contact with aqueous and fatty foods	177.1400	Hydroxyethyl cellulose film, water-insoluble
176.180	Components of paper and paperboard in contact with dry food	177.2470	Polyoxymethylene copolymer
		177.2480	Polyoxymethylene homopolymer

(03/12/09)JMB/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.