



Schill + Seilacher

Struktol Company of America

201 East Steels Corners Road
P.O.Box 1649, Stow, OH 44224-0649
(330) 928-5188 • (800) 327-8649



www.struktol.com • customerservice@struktol.com

Technical Data Sheet

STRUKTOL® TS 30

STRUKTOL® TS 30-DL

STRUKTOL® TS 35

STRUKTOL® TS 35-DL

Tackifiers and Softeners

Composition		STRUKTOL TS 30	STRUKTOL TS 30-DL	STRUKTOL TS 35	STRUKTOL TS 35-DL
Aliphatic-aromatic soft resin		100 %	67 %	100 %	67 %
Silica		--	33 %	--	33 %
Properties		STRUKTOL TS 30	STRUKTOL TS 30-DL	STRUKTOL TS 35	STRUKTOL TS 35-DL
Appearance		light yellowish viscous substance	light yellowish, crumbly powder	clear viscous substance	light crumbly powder
Density	[kg/m ³]	1000	1200	1000	1200
Bulk density	[kg/m ³]		650		600
Viscosity at 100 °C	[mPa·s]	2200	--	80	
Ash content	[%]	--	32	--	32
Physiological behaviour		refer to safety data sheet			
Storage stability		at least 24 months under normal storage conditions			
Packing		1 kg PE- sachets with a low melting point	25 kg bags	200 kg drums	25 kg bags

STRUKTOL TS 30 and STRUKTOL TS 35 are soluble in aromatic and chlorinated hydrocarbons, while there is only limited solubility in aliphatic hydrocarbons and mineral oils.

The data given are typical values which are not intended for use in preparing specifications. For test methods refer to the corresponding supplement.

Schill + Seilacher "Struktol"
Aktiengesellschaft
Moorfleeter Str. 28
22113 Hamburg
GERMANY

Phone: +49 40 73 36 2-0
Fax: +49 40 73 36 2-194
E-Mail: info@struktol.de

www.struktol.de



