



STRUKTOL[®] V-EGS

PROCESSING ADDITIVE

COMPOSITION

Ethylene glycol distearate

PROPERTIES	TYPICAL VALUES
Appearance	White to light yellow pastille or powder
Dropping point (°C)	63 - 73
Specific Gravity (g/cm ³)	.93
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] V-EGS is a very compatible internal/external lubricant for rigid PVC. It is particularly useful in rigid PVC extrusion such as window, siding and other profiles.

STRUKTOL[®] V-EGS is also good in injection molding formulations.

DOSAGE

Typical dosage is between 0.5 – 1.5 phr

FDA STATUS

STRUKTOL[®] V-EGS is sanctioned for use by the Food and Drug Administration (FDA) in a number of applications, listed in the following sections of Title 21 of the Code of Federal Regulations:

- 73.1 Diluents in Color Additives Mixtures for Food Use Exempt from Certification
- 175.300 Resinous and polymeric coatings
- 176.210 Defoaming agents used in the manufacture of paper and paperboard