



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] V-EGS

PROCESSING ADDITIVE

COMPOSITION

Ethylene glycol distearate

TYPICAL PROPERTIES

Appearance	White to beige pastille or powder
Dropping point (C)	63 - 73
Specific Gravity	.93
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] V-EGS is very compatible internal/external lubricant for rigid PVC. It is an excellent lubricant for rigid PVC extrusion such as window, siding and other profiles.

STRUKTOL[®] V-EGS is also good in injection molding formulations.

DOSAGE

Typical dosage is between 0.5 – 1.5 phr

(01/21/09)JMB/rca