



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL® V-PEAS

LUBRICANT ADDITIVE FOR PVC AND POLYMER PROCESSING

COMPOSITION

Polymeric complex ester of saturated fatty acids.

PROPERTIES

Appearance	Off-white pastille or powder
Acid Value	5 - 15
Melting Point (°C)	40 - 50
Specific Gravity	1.017
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 year under normal storage conditions
Packaging	55 lb. bag

RECOMMENDATIONS FOR APPLICATION

Typical Applications: STRUKTOL® V-PEAS is a very compatible complex ester lubricant and is especially suited for calendared PVC sheet. It also has application in extrusion, blow molding and injection molding formulations.

Features: STRUKTOL® V-PEAS is a very effective lubricant with externally lubricating properties which has no negative impact on clarity in extrusion, calendaring, or injection molding. STRUKTOL® V-PEAS is noted to have ideal characteristics for clear applications where clarity is critical and where lower cost in performance is needed to replace montanic esters.

DOSAGE

Injection Molding (Opaque)	V-SSE	0.7 – 1.0 phr	Extrusion (Opaque)	V-SSE	0.7 – 1.0 phr
	V-PEAS	0.3 – 0.5 phr		V-PEAS	0.3 – 0.7 phr
	Calcium Stearate*	0.7 – 1.0 phr		Calcium Stearate	0.7 – 1.0 phr
	V-HRW	0.7 – 1.5 phr		V-HRW	0.7 – 1.0 phr
	V-PEAS	0.3 – 0.75 phr		V-PEAS	0.3 – 0.75 phr
	Oxidized HDPE	0.07 – 0.15 phr		Oxidized HDPE	0.07 – 0.15 phr
	Calcium Stearate*	0.3 – 1.0 phr		Calcium Stearate	0.3 – 0.75 phr
*Note: Reduce Calcium Stearate as much as possible for improved flow.					
Injection Molding (Clear)	V-HRW	0.7 – 1.0 phr	Extrusion (Clear)	V-DSP	0.7 – 1.0 phr
	V-PEAS	0.3 – 0.6 phr		V-PEAS	0.3 – 0.6 phr
				Oxidized HDPE	0.1 – 0.3 phr

-over-



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

DOSAGE - CONTINUED

Calendering <i>(Opaque)</i>	V-HRW	0.7 – 1.5 phr
	V-PEAS	0.3 – 0.6 phr
	Oxidized HDPE	0.07 – 0.15 phr
	Calcium Stearate	0.3 – 0.75 phr

Calendering <i>(Clear)</i>	V-HRW	0.6 – 1.2 phr
	V-PEAS	0.3 – 0.5 phr

FDA STATUS

STRUKTOL[®] V-PEAS is sanctioned for use by the Food and Drug Administration (FDA) in a number of applications, listed in the following section of Title 21 of the Code of Federal Regulations: **178.3690**

(03/21/2012)ZB/JMB/mmm