



# **STRUKTOL<sup>®</sup> WB 900A**

**SCORCH INHIBITOR**

## **COMPOSITION**

Magnesium Oxide Dispersion

---

## **TYPICAL PROPERTIES**

---

Appearance	tan bead
Magnesium Oxide (%)	75 ± 1
Specific Gravity	2.09
Physiological Behavior	refer to safety data sheet
Storage Stability	at least 1 year under normal storage conditions
Packaging	55 lb. cardboard box

---

## **RECOMMENDATIONS FOR APPLICATION**

Struktol metal oxide preparations may be used in rubber compounds where the dispersion of untreated metal oxides gives rise to problems. They reduce sticking to the rotor blades and mill rolls.

STRUKTOL<sup>®</sup> WB 900A provides protection against humidity and carbon dioxide.

STRUKTOL<sup>®</sup> WB 900A reduces the scorch risk of polychloroprene compounds.

## **DOSAGE**

1 part by weight of magnesium oxide corresponds to 1.33 parts of STRUKTOL<sup>®</sup> WB 900A.