



## RUBBER SERVICE SRL

### *Antiadherente Liquido*

#### Aqueous Dispersion of **Antiadherente P**

This pre-dispersed material presents itself as an appropriate solution for those businesses that do not possess the necessary equipment for the correct dispersion of **Antiadherente P** in water.

The pre-dispersion state of **Antiadherente Liquido** allows a rapid dilution of the concentrations to be used, simply by adding the necessary quantity to water at room temperature and homogenizing it by shaking or stirring gently.

The instructions for use are the same as detailed in the sheet corresponding to **Antiadherente P**.

#### Properties:

Composition: Aqueous Dispersion of **Antiadherente P**

Concentration: 18 - 22% of solids

Ph: 7.5 – 10.5

Solvent: Water

Viscosity: 0.5 - 2.5 minutes in Glass Fort No 2 to 25° C

#### Dosage:

The addition of 6% to 12% weight of **Antiadherente Liquido** in water will be sufficient to produce a film that will prevent the sticking of slabs for the majority of the common compounds in the industry.

#### Observations:

The very fine anti-adherent film that is deposited on the raw mixtures is absolutely compatible with the rubber and does not produce adhesion fault inconveniences during vulcanization.

#### Packaging:

**Antiadherente Liquido** is available in drums of 200 kg and cans of 20 kg.

Stability: Approximately 24 months.



#### **Distributed By:**

Struktol Company of America  
201 E. Steels Corners Road  
P.O. Box 1649 • Stow, Ohio 44224-0649  
(330) 928-5188 • (800) 327-8649  
www.struktol.com  
customerservice@struktol.com

**Quality Additives for Performance**

Las recomendaciones para el uso de nuestros productos están basadas en tests considerados confiables. Sin embargo Rubber Service SRL no garantiza los resultados a ser obtenidos por otros bajo diferentes condiciones. Nada en este folleto es entendido como un intento de infringir cualquier patente.

Besares 4585 (1702) Ciudadela, Buenos Aires, Argentina  
Teléfono : 54-11-4657-2992 Fax : 54-11-4657-5040

**www.rubberservice.com.ar**



Producers of Specialty Chemicals

# Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649 • Stow, Ohio 44224-0649  
www.struktol.com

## Antiadherente Liquid Dilution Chart

*Product Supplied as 20% Solids  $\pm$  1.5%*

### 50 GALLON TANK

Solids	Dilution	Product Pounds	Water Pounds	Total Pounds
1.00%	19.01:1	20.82	395.68	416.50
2.00%	9.00:1	41.64	374.86	416.50
3.00%	5.67:1	62.52	353.98	416.50
4.00%	4.00:1	83.36	333.14	416.50
5.00%	3.00:1	104.10	312.40	416.50
6.00%	2.33:1	124.92	291.58	416.50
7.00%	1.86:1	145.74	270.76	416.50
8.00%	1.50:1	166.56	249.94	416.50
9.00%	1.22:1	187.38	229.12	416.50
10.00%	1.00:1	207.30	209.20	416.50

Recommended Usage: 1.50% to 2.00% Solids

STP0257  
(01/08/2008)LCL

Phone: (330) 928-5188  
Fax: (330) 928-8726



Technical Services: 1-800-327-8649  
E-mail: customerservice@struktol.com