



## Struktol Company of America, LLC

201 E. Steels Corners Road • Stow, Ohio 44224-4921

Phone (330) 928-5188 • Fax (330) 928-0013

www.struktol.com • customerservice@struktol.com

## TECHNICAL DATA

# STRUKTOL<sup>®</sup> SCA 930 CB

### COUPLING AGENT

### COMPOSITION

A 1:1 blend of N 330 carbon black and a bifunctional silane.

<i><b>PROPERTIES</b></i>	<i><b>TYPICAL VALUES</b></i>
Appearance	Black microbeads
Ash (% , max.)	12.8 ± 0.8
Chloride Content (% , max.)	7.2 ± 0.5
Specific Gravity (g/cm <sup>3</sup> )	1.30
Storage Stability	1 year under normal storage conditions
Packaging	55 lb. box

### RECOMMENDATIONS FOR APPLICATION

STRUKTOL<sup>®</sup> SCA 930 CB is used in halogenated elastomers compounded with silica, clay, or talc.

### DOSAGE

Suggested dosage per 100 parts of filler:

For silica - 6 – 26 parts

For clay and talc - 1 – 2 parts

(08/19/05)AAC/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.