



## Struktol Company of America, LLC

201 E. Steels Corners Road • Stow, Ohio 44224-4921

Phone (330) 928-5188 • Fax (330) 928-0013

www.struktol.com • customerservice@struktol.com

## TECHNICAL DATA

# STRUKTOL<sup>®</sup> SCA 989

## COUPLING AGENT

### COMPOSITION

Mercaptopropyltriethoxysilane

PROPERTIES	TYPICAL VALUES	
	SCA 989	SCA 989 WT
Appearance	Colorless liquid	Light gray powder
Alcohol Content (%)	≤ 1.0	< 1.0
SCA 989 Content (%)	≥ 95	68 - 72
Specific Gravity (g/cm <sup>3</sup> )	1.00	1.20
Storage Stability	At least two years under normal storage conditions	At least 6 months at room temperature in original sealed container
Packaging	55 lb pail 440 lb drum 2200 lb tote	200 lb drum

### RECOMMENDATIONS FOR APPLICATIONS

STRUKTOL<sup>®</sup> SCA 989 is used to improve the reinforcing capability of fillers with silanol groups on their surface (e.g., silicas, silicates, clays, etc.). STRUKTOL<sup>®</sup> SCA 989 can improve tensile strength, tear strength and abrasion resistance and reduce compression set of vulcanizates.

### DOSAGE

Suggested dosage per 100 parts of filler:	<u>SCA 989</u>	<u>SCA 989 WT</u>
For silica:	2.0 – 8.0 parts	3.0 – 11.0 parts
For clay and talc:	0.5 – 1.0 parts	0.7 – 1.4 parts

(08/23/05)AAC/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.