



## Struktol Company of America, LLC

201 E. Steels Corners Road • Stow, Ohio 44224-4921

Phone (330) 928-5188 • Fax (330) 928-0013

www.struktol.com • customerservice@struktol.com

## TECHNICAL DATA

# STRUKTOL<sup>®</sup> SU 95AF

## PREPARATIONS OF SOLUBLE SULFUR

### COMPOSITION

Sulfur	95%
Organic Dispersing Agent	5%

### PROPERTIES

### TYPICAL VALUES

Appearance	Powder
Flash Point (°C)	207
Specific Gravity (g/cm <sup>3</sup> )	1.92
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. box / 1,980 lb. skid 25 kg. box / 900 kg. skid

### RECOMMENDATIONS FOR APPLICATION

STRUKTOL<sup>®</sup> 95AF are coated soluble sulfurs containing dispersing agents and wetting agents.

Incorporation and dispersion of the sulphur takes place without formation of agglomerates and local concentrations. Development of dust as well as electrostatic charges of the sulphur are avoided thus providing greater production safety as regards to possible risks of fire or explosion.

Struktol coated sulfurs can be applied in any natural rubber and synthetic rubber compound that is sulfur cured. The dispersing agents used have no influence on cure and do not discolor the vulcanizate.

### DOSAGE

1 phr

(02/15/2008Rev1)JDC/abw