

Phone (330) 928-5188 • Fax (330) 928-0013 www.struktol.com • customerservice@struktol.com



STRUKTOL[®] TPW 813

COMPATABILIZER / COUPLING AGENT

COMPOSITION

Proprietary blend.

PROPERTIES	TYPICAL VALUES
Appearance	White to off white pastille
Melting Point (°C)	79 - 87
Specific Gravity (g/cm ³)	1.2
Physiological Behavior	Refer to safety data sheet
Storage Stability	1 year under normal storage conditions in original sealed container.
Packaging	50 lb. bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TPW 813 next generation coupling agent for use in wood plastic composites (WPC). It offers superior properties vs. traditional coupling agents. In addition to providing excellent flexural properties, it is especially effective at reducing water absorption, resulting in a much more durable product that can withstand many more wetting and freeze-thaw cycles. It does react chemically so it is recommended that the extruder have a vacuum vent or at minimum, an atmospheric vent. Extruder temperatures of minimum 170°C are recommended.

It is also notable that STRUKTOL[®] TPW 813 can be used with any type of lubricant and works especially well with STRUKTOL[®] TPW 617, a next generation high efficiency lubricant/process aid.

STRUKTOL[®] TPW 813 may continue to react in the extruded product so it is recommended to wait at least 48 hours before measuring flexural or other physical properties to obtain the final values.

DOSAGE

0.5 - 1.5%

(10/26/2023)MTM/rca