

# Struktol Company of America, LLC 201 E. Steels Corners Road • Stow, Ohio 44224-4921

201 E. Steels Corners Road • Stow, Ohio 44224-4921 Phone (330) 928-5188 • Fax (330) 928-0013 www.struktol.com • customerservice@struktol.com



# STRUKTOL® V-SSE

LUBRICANT ADDITIVE FOR PVC AND POLYMER PROCESSING

#### **COMPOSITION**

Fatty acid ester.

PROPERTIES	TYPICAL VALUES		
Appearance	Pastille		
Melting Point (°C)	54 - 61		
Specific Gravity	0.935		
Physiological Behavior	Refer to safety data sheet		
Storage Stability	At least 2 year under normal storage conditions		
Packaging	55 lb. bag / 2,200 lb. skid 25 kg. bag / 1,000 kg. skid		

## **RECOMMENDATIONS FOR APPLICATION**

**Typical Applications:** STRUKTOL® V-SSE has both internal and external lubricant characteristics. It is used in calendering, extrusion and injection molding applications. It also has excellent applicability in extruded complex profile.

**Features:** STRUKTOL® V-SSE is noted for superior weathering characteristics. STRUKTOL® V-SSE is also noted for its ability to reduce melt viscosity in both injection molding and extrusion. STRUKTOL® V-SSE is particularly resistant to plate out and is noted for its ability to improve printability of extruded parts (particularly when substituting for paraffin).

### **DOSAGE**

Injection Molding (Opaque)	V-SSE V-PEAS Calcium Stearate*	0.7 - 1.0  phr 0.3 - 0.5  phr 0.7 - 1.0  phr	Extrusion (Opaque)	V-SSE V-PEAS Calcium Stearate	0.7 - 1.0  phr 0.3 - 0.7  phr 0.7 - 1.0  phr
	*Note: Reduce Calcium Steara	ite as much as possible	e for improved flow.	V-SSE VLB-602 Calcium Stearate	0.7 – 1.0 phr 0.4 – 0.8 phr 0.7 – 1.0 phr

(03/31/2022)JDC/abw