



Struktol Company of America, LLC

201 E. Steels Corners Road • Stow, Ohio 44224-4921

Phone (330) 928-5188 • Fax (330) 928-0013

www.struktol.com • customerservice@struktol.com

**TECHNICAL
DATA**

STRUKTOL[®] WB 900A

SCORCH INHIBITOR

COMPOSITION

Magnesium Oxide Dispersion

PROPERTIES	TYPICAL VALUES
Appearance	Tan bead
Magnesium Oxide (%)	75 ± 1
Specific Gravity	2.09
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 1 year under normal storage conditions
Packaging	55 lb. cardboard box

RECOMMENDATIONS FOR APPLICATION

Struktol metal oxide preparations may be used in rubber compounds where the dispersion of untreated metal oxides gives rise to problems. They reduce sticking to the rotor blades and mill rolls.

STRUKTOL[®] WB 900A provides protection against humidity and carbon dioxide.

STRUKTOL[®] WB 900A reduces the scorch risk of polychloroprene compounds.

DOSAGE

1 part by weight of magnesium oxide corresponds to 1.33 parts of STRUKTOL[®] WB 900A.

(08/07/09)LCL/rca